

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 197 971 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
17.04.2002 Bulletin 2002/16

(51) Int Cl.7: **H01B 3/44, H01B 3/22**

(21) Application number: **00500210.0**

(22) Date of filing: **10.10.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(71) Applicant: **Dynasol Elastomeros, S.A.**
28046 Madrid (ES)

(72) Inventors:
• **Barrio Calle, Juan Antonio**
28026 Madris (ES)

- **Gonzalez Gonzalez, Carlos**
28042 Madrid (ES)
- **Prieto Noguera, Juan Antonio**
28925 Alcorcon (Madrid) (ES)

(74) Representative: **Del Santo Abril, Natividad**
Oficina Garcia Cabrerizo, S.L.,
Vitruvio, 23
28006 Madrid (ES)

(54) **Composition for cables filling**

(57) The invention relates to compositions for cables filling wherein a styrene-butadiene block copolymer with radial structure is used as a gelling agent. This polymer is obtained through styrene and butadiene sequential polymerization and subsequent reaction with a coupling agent preferably of type $Cl_{4-n}MR_n$, wherein M = Sn or Si, R is an alkyl or aryl group and n is an integer

from 0 to 2, and hydrogenation of the resulting polymer. This type of copolymer brings a higher stability to the final properties of the gel as compared with the linear hydrogenated synthetic rubbers usually used in the prior art.

EP 1 197 971 A1

Description

SUMMARY OF THE INVENTION

5 [0001] The present invention relates to the formulation of compositions for cables filling used in telecommunication, more specifically it relates to the use in these compositions of a hydrogenated radial styrene-butadiene block copolymer.

STATE OF THE ART

10 [0002] The use of synthetic rubbers in the formulation of waterproof compounds used in communication cables filling is known, the aim of these synthetic rubbers is to act as gelling agents, effective in the formation of a crystalline structure stable during long storage periods and in different temperature conditions.

[0003] On the other hand, the cables filling compositions of the prior art formulated with synthetic rubber show an excellent behavior as an anti-humidity barrier, avoiding the penetration of contaminators and protecting the cable from the breaking due to mechanical efforts during its handling. Due to their suitable viscosity, they can be injected at low temperature, filling the interstices of the cable and giving to the final product characteristics suitable as a support of the wires.

[0004] Examples of this type of formulations can be found in different patents: EP 0749128, US 5358664, US 4810395, US 5348669, EP 0236918 and WO 97/04465.

20 [0005] The formulation of these compositions is realized by using mainly refined mineral basis or synthetic basis with the addition of synthetic rubbers (usually hydrogenated), and optionally polyethylene waxes and anti-oxidant additives.

[0006] However, these formulations show the problem that they are very sensitive to the variations of the waxes used in the formulation. Especially the Drip-Test value, that calculates the gel stability in time and at different temperatures. So, for compositions with the same proportions of synthetic rubber, a change in crystallinity in the polyethylene wax can seriously affect the stability of these compounds.

[0007] As a consequence, there is the need of a composition for cables filling that shows improved stability over the compositions of the prior art.

30 [0008] It has been surprisingly found that the use of a radial hydrogenated styrene-butadiene block copolymer in the formulation of cables filling compounds not only improves the Drip-Test values, but also substantially improves the stability of the compositions.

SUMMARY OF THE INVENTION

35 [0009] The invention concerns compositions for cables filling wherein a hydrogenated styrene-butadiene block copolymer with radial structure is used as a gelling agent. This polymer is obtained through styrene and butadiene sequential polymerization and subsequent reaction with a coupling agent preferably of type $Cl_{4-n}MR_n$, wherein M = Sn or Si, and hydrogenation of the resulting polymer.

DETAILED DESCRIPTION OF THE INVENTION

[0010] The object of the present invention is the provision of compositions for cables filling that show an improved stability.

45 [0011] The composition for cables filling of the present invention is characterized by the use of a hydrogenated styrene-butadiene block copolymer with a radial structure (radial SEES), obtained through coupling.

[0012] The composition comprises: from 70 to 90% of a mineral or synthetic oil, from 0 to 12% of a polyethylene wax, 2 to 15% of radial SEES synthetic rubber.

50 [0013] The radial copolymer can be synthesized through known methods, for example by anionic polymerization catalyzed by butyllithium. In this case, a polymer is prepared by sequential polymerization of a vinyl aromatic monomer (e.g. styrene) and a conjugated diene monomer (e.g. butadiene). A lithium atom ends the chain of the polymer. In this way it is possible to go on polymerizing or reacting with other compounds as in the case of a coupling agent. The coupling agents for polymer chains are known in the art, as for CO_2 , dihaloalkanes, divinylbenzene, carbonates, chlorides, etc. The use of agents, whose functionality is higher than two, allows the formation of radial polymers. The preferred coupling agents of the invention are of type $Cl_{4-n}MR_n$, wherein M = Sn or Si, R is an alkyl or aryl group and n is an integer from 0 to 2, and the most preferred are those having a theoretic functionality equal to four and more concretely Cl_4Si or Cl_4Sn .

55 [0014] The structure of the butadiene block has preferably a vinyl content sufficient so that, when hydrogenating the polymer, this continues to be soluble in the reaction medium and the resulting polymer maintains its elastomeric prop-

erties. More specifically the vinyl content is preferably higher than 25% more preferably higher than 30% and most preferably between 35 and 45% based on the polybutadiene fraction. A known method to achieve these percentages of vinyl addition is the use of polymerization polar modifiers known in the art, such as quaternary amines, ethers, etc...

[0015] The styrene content in the copolymer is preferably between 20 and 40%, more preferably between 25 and 35% of styrene.

[0016] The coupling percentage of the styrene butadiene chains is not a critical parameter, it should however be sufficient to give the properties of a radial polymer. Preferably more than 80% of the chains and more preferably more than 90% of the chains are coupled.

[0017] The polymer final molecular weight is such that the resulting composition viscosity is as low as possible in order to be easily injectable. For this reason the molecular weight of the polymer of the invention is preferably between 30,000 and 110,000 and more preferably between 60,000 and 90,000. A too low molecular weight would not give the desired properties without adding a higher quantity of polymer, thus increasing the cost of the formulation, while a too high molecular weight would lead to viscous formulations that are difficult to be injected at room temperature and would require a higher amount of energy.

[0018] The polymers hydrogenation can be done through the methods known in the art, more preferably by a homogeneous hydrogenation process, under moderate pressure and temperature conditions, that avoids breaking of the coupled polymer chains. More preferably a metallocene catalyst is used that does not require the step of separation of the catalyst from the polymer. The most preferred hydrogenation processes used in the present invention are those described in EP 0601953 and EP 0885905, though they do not limit the present invention.

[0019] Suitable oil to be used in the present invention are polybutene oils and mineral oils such as naphthenic oils and paraffinic oils, triglyceride based oils (such as castor oil), polypropylene and polypropylene glycol oils. It is also possible to use mixtures of the above oils. Preferred oils or oil compositions have a viscosity at 100°C between 2 and 6 cSt.

[0020] The composition can also comprise up to 12% by weight of a polyethylene wax. Preferred polyethylene waxes have a melting point comprised between 90 and 120°C.

[0021] The composition can also comprise other components, such as antioxidants, dyes, fungus inhibitors.

[0022] In a preferred embodiment, the composition comprises from 0.05 to 0.4% by weight of an antioxidant.

[0023] What follows are some explanatory examples of the composition object the invention, that show the advantage of using radial SEBS as compared to linear SEES sythetic rubbers. These examples do not imply any limitation of the scope of the invention.

EXAMPLES

Synthesis of a radial SEES

[0024] In a 2 liter stainless steel stirred reactor, 1200 ml of cyclohexane, 233 ml of a 18.2% by weight solution of styrene in cyclohexane and 6.4 ml of tetrahydrofurane were introduced in a N₂ atmosphere. They were warmed up to 70°C and 17 ml of a 3% solution of n-butilithium in cyclohexane were added as the polymerization initiator. They were left reacting for 25 minutes to form a polystyrellithium chain, then 128 ml of butadiene were added and they were left reacting for 25 more minutes. At the end of this time 1.5 mmoles of Cl₄Si were added to the reactor and it was left reacting for 5 minutes.

[0025] A sample was collected for analysis and what resulted was an SES polymer with a styrene content of 30%, a vinyl addition in butadiene of 40% and an average molecular weight by number of 75,000. The amount of coupled chains was 92%.

[0026] The polymer was subjected to hydrogenation by using Cp₂Ti(4-OMe-Ph)₂, as described in EP 0601953 and EP 0885905. The hydrogenation reaction was carried out in the same vessel where polymerization was performed. The initial temperature for hydrogenation was 90°C, the hydrogen pressure was 10 kg/cm² and the total amount of hydrogenation catalyst used was 0.22 mmol/100g polymer. The hydrogenation proceeded until the hydrogen flow fell down to zero in 30 minutes, the percentage of hydrogenation was higher than 99% of the olefinic double bounds without any hydrogenation of the styrene units. The resulting hydrogenated SBS, called SEES, was further isolated from the reaction medium through elimination of the solvent with steam and further drying of the polymer in an oven.

Comparative example 1

[0027] A formulation with a basis of mineral oil with linear SEES sythetic rubber (KG 1652™ by Shell) and polyethylene wax AC-9™ by Allied (group 1, characteristics table 1) in the proportions that are shown in Table 2, shows a Drip Test value FTM-791, % by weight (70°C 24h) = 10.5.

EP 1 197 971 A1

Comparative example 2

[0028] A formulation is realized with a basis of mineral oil with linear SEES synthetic rubber (Calprene-H 6110™ by Repsol Química) and polyethylene wax by Allied AC-9 (group 1) in the proportions of the compositions of Table 2, shows a Drip Test value FTM-791, % by weight (70°C 24h) = 9.8

[0029] In examples 1 and 2 it is shown how lower Drip Test values are obtained by using coupled SEES synthetic rubbers

Example 1

[0030] A formulation is realized with a basis of mineral oil with a coupled SEES synthetic rubber, Sample A1, in the proportions of the compositions of Table 2 and polyethylene wax by Allied AC-9™ (group 1), has a Drip Test value FTM-791 of 2.4% by weight (70°C 24h).

[0031] The characteristics of Sample A1 are: content of styrene 33,0% by weight, coupled with Cl₄Si, approximate molecular weight 80,000 and content of 1,2 polybutadiene before hydrogenating 40% based on the butadiene fraction.

Example 2

[0032] A formulation is realized with a basis of mineral oil with a coupled SEES synthetic rubber, Sample A2, in the proportions of the compositions of Table 2 and polyethylene wax by Allied AC-9™ (group 1), shows a Drip Test value FTM-791 of 3.8% by weight (70°C 24h)

[0033] The characteristics of sample 2 are: content in styrene 30.6% by weight, coupled with Cl₄Si, approximate medium molecular weight 83,000 and content in 1,2 polybutadiene before hydrogenating 40.6%.

Example 3

[0034] In example 3 it is shown that the final properties of the compositions of the invention do not change with the crystallinity of the waxes used, in contrast with the behavior of compositions based on a conventional linear synthetic rubber.

[0035] Compositions are realized in the proportions that are shown in Table 2, wherein while keeping the proportions steady, the polyethylene wax is changed, the main difference being crystallinity. In Table 2 it is shown how the Drip Test values of the composition with linear SEES worsen (increase) when the polyethylene wax is changed, while the values of the compositions realized with a radial SEBS are essentially the same.

[0036] The main characteristics of the polyethylene waxes groups AC-9™ used are shown in Table 1, by measuring the difference in crystallinity both by Diffraction of X Rays (DRX) and by differential Calorimetry (DSC):

Table 1

		Group 1	Group 2
Crystallinity DRX (FWHM) %:			
	Peak 110	0.64	0.78
	Peak 200	0.82	0.93
Molecular w. (GPC)⁽⁵⁾			
	Mn	3000	2790
	Mw	7340	6850
	Mz	13000	12700
	Mw/Mn	2.45	2.46
Chromatography			
	C18-C70%	48.3	61.2
	>C70%	51.7	38.8
DSC			
	H1(J/g)	176	153

Table 1 (continued)

		Group 1	Group 2
DSC			
	H2(J/g)	166	151
FWDH: Full Width Half Maximum GPC: Gel Permeation Chromatography			

Table 2

	Test 1	Test 2	Test 3	Test 4
Composition				
Mineral oil	87.3	87.3	87.3	87.3
Linear SEBS Synthetic rubber (Kraton G-1652™)	4.9	4.9	-	-
Coupled SEBS Synthetic rubber (sample A1)	-	-	4.9	4.9
Wax AC-9™ (group 1)	5.0	-	5.0	-
Wax AC-9™ (group 2)	-	5.0	-	5.0
Additives rest	2.8	2.8	2.8	2.8
Properties				
Melting point, °C ASTM-D-127	98.4	98.2	98.8	97.6
Viscosity at 120°C, cSt ASTM-D-445	27.9	28.6	29.9	30.2
Drip-Test at 70°C/24h FTM-791	7.1	11.9	3.8	3.9

Claims

1. Composition for cables filling comprising a mineral or synthetic oil and a radial hydrogenated SEBS synthetic rubber.
2. A composition according to claim 1 further comprising a polyethylene wax.
3. The composition of claim 1 or 2 wherein the proportions of the components are: mineral oil from 70 to 90% and radial hydrogenated SEBS synthetic rubber from 2 to 15% and from 0 to 12% by weight polyethylene wax.
4. The composition of anyone of claims 1 to 6 wherein the styrene butadiene radial copolymer is synthesized through coupling with Cl₄Si or Cl₄Sn.
5. The composition of anyone of claims 1 to 4 wherein the copolymer used has a content in styrene comprised between 20 and 40% by weight.
6. The composition of anyone of claims 1 to 5 wherein the vinyl content in the SEES rubber used is higher than 25%.
7. The composition of anyone of claims 1 to 6 wherein the polymer molecular weight is comprised between 30,000 and 110,000.
8. Use of a composition according to anyone of claims 1 to 7 as a cable filling material.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 50 0210

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	EP 0 822 227 A (SHELL INT RESEARCH) 4 February 1998 (1998-02-04) * page 4, line 20 - line 43 * * page 5, line 45 - line 56; claims 1-8 * ---	1-8	H01B3/44 H01B3/22
A	US 4 324 453 A (PATEL NAREN I) 13 April 1982 (1982-04-13) * column 4, line 6 - column 5, line 13; claims 1,2; example 6; table 3 * ---	1-8	
A	GB 2 109 949 A (WESTERN ELECTRIC CO) 8 June 1983 (1983-06-08) * claims 1,2; example 2; tables 1,3 * ---	1-8	
A	US 4 219 627 A (HALASA ADEL F ET AL) 26 August 1980 (1980-08-26) * claims 1-4; examples 1,5 * -----	1,4-7	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			H01B C08L G02B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 17 January 2001	Examiner Lehnert, A
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 50 0210

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-01-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0822227 A	04-02-1998	BR 9705233 A	29-06-1999
		CA 2211944 A	31-01-1998
		JP 10077382 A	24-03-1998
		US 5926707 A	20-07-1999
US 4324453 A	13-04-1982	US 4351913 A	28-09-1982
GB 2109949 A	08-06-1983	US 4432607 A	21-02-1984
		US 4492428 A	08-01-1985
		CA 1175718 A	09-10-1984
		DE 3239818 A	05-05-1983
		FR 2519775 A	18-07-1983
		JP 58100102 A	14-06-1983
		NL 8204136 A	16-05-1983
US 4219627 A	26-08-1980	NONE	